

# PRODUCT DATA SHEET

n° of certification organisation: 0679  
Year mark was 1<sup>st</sup> fixed : 2006

## HYRENE (HYRANGER) 25/25 RE

### DESCRIPTION

HYRANGER 25/25 RE is a glass-fibre reinforced SBS elastomeric modified bituminous waterproofing membrane.

### USE

Vapour control layer on concrete, cellular concrete and timber. First or second layer in multi-layer HYRENE (HYRANGER) waterproofing system for flat roofs.

### APPLICATION METHOD

Torched or pour and roll.

### STORAGE

Rolls to be stored upright and away from heat.

### COMPOSITION

(indicative)

Reinforcement (gm/m <sup>2</sup> ) :	Glass-fibre	50
Binder (gm/m <sup>2</sup> ) :	SBS elastomer	2,670
Surface finish (gm/m <sup>2</sup> ) :	Sand	1,000
Under surface finish (gm/m <sup>2</sup> ) :	Sand	300

### CHARACTERISTICS

	STANDARD(BS)	UNITS	VALUES	Tolerance		
				Min	Max	
Dimensions	EN 1848-1	Length	10	-1%		
		Width	1	-1%		
		Straightness	Pass			
	EN 1849-1	Nominal roll weight	33.8			
		Thickness (selvedge)	2.65	2.50	2.80	
Visible defects	EN 1850-1	New product	None			
		After ageing to EN 1297	NA			
Adhesion of granules	EN 12039	%	NA	-	-	
Resistance to tearing (nail shank)	EN 12310-1	Longitudinal	80	50	130	
		Cross direction	80	50	130	
Tensile properties : maximum tensile force	EN 12311-1	Longitudinal	250	200	500	
		Cross direction	150	120	280	
Tensile properties : elongation	EN 12311-1	Longitudinal	3	2	4	
		Cross direction	3	2	4	
Peel resistance of joint	EN 12316-1	Maximum force	Selvedge	NA	-	-
			End joint	NA	-	-
		Average force	Selvedge	NA	-	-
			End joint	NA	-	-
Shear resistance of joint	EN 12317-1	Maximum force	Selvedge	NA	-	-
			End joint	NA	-	-
Flexibility at low temperature	EN 1109	Surface	-16	≤		
		Under surface	-16	≤		
Flow resistance at elevated temperature	EN 1110	New product	100	≥		
		After ageing to EN 1296	NA			
Resistance to impact	EN 12691	mm	30	≤		
Resistance to static loading	EN 12730 (A)	kg	PND	≥		
Dimensional stability	EN 1107-1	%	0.1	≤		
Form stability under cyclic temperature change	EN 1108	%	NA			
Water vapour transmission properties	EN 1931	New product	285			
		After ageing to EN 1296	290			
Watertightness	EN 1928	New product	Pass	<10 kPa		
		After ageing to EN 1296	NA			
Watertightness after stretching at low temperature	EN 13897	%	NA			
Reaction to fire	EN 13501-1	-	F			
Resistance to root penetration	EN 13948	-	NA			
Dangerous substances consult : <a href="http://europa.eu.int/comm/enterprise/construction/internal/dangsub/dangmain.htm">http://europa.eu.int/comm/enterprise/construction/internal/dangsub/dangmain.htm</a>	-	-	None			

NA=not applicable due to use of product. PND=Performance not determined.

The manufacturer reserves the right to modify, at any time, the characteristics of its products.