



Technical Data Sheet

Datasheet 30.06.10
Product Code: 1553001

Axter Limited

West Road Ransomes Europark
Ipswich Suffolk IP3 9SX
Tel (01473) 724056 Fax (01473) 723263
Email info@axterltd.co.uk

www.axter.co.uk

NB: The manufacturer reserves the right without prior notice to modify the composition of his products. Characteristics provided in this publication derive from data obtained under controlled test conditions. AXTER Limited makes no warranties, express or implied as to the properties and performance under any variations from such conditions in actual construction.

35 PY REINFORCEMENT STRIP

INTRODUCTION	35 PY REINFORCEMENT STRIP is a polyester reinforced SBS elastomeric membrane. Its minimal thickness is 3.5 mm.								
USAGE	Detail reinforcement strips for application to: upstands, perimeters, pipes and other penetration details.								
PACKAGING	Rolls of 10 ml (10 m x 0.25 m) with an average weight of 11 kg.								
STORAGE	Rolls to be stored upright and under cover.								
COMPOSITION	<table> <tr> <td>Polyester reinforcement.....</td> <td>150 gm/m²</td> </tr> <tr> <td>SBS elastomeric binder.....</td> <td>3900 gm/m²</td> </tr> <tr> <td>Finishing: surface film.....</td> <td>10 gm/m²</td> </tr> <tr> <td>underside sand.....</td> <td>300 gm/m²</td> </tr> </table>	Polyester reinforcement.....	150 gm/m ²	SBS elastomeric binder.....	3900 gm/m ²	Finishing: surface film.....	10 gm/m ²	underside sand.....	300 gm/m ²
Polyester reinforcement.....	150 gm/m ²								
SBS elastomeric binder.....	3900 gm/m ²								
Finishing: surface film.....	10 gm/m ²								
underside sand.....	300 gm/m ²								
CHARACTERISTICS <i>binder</i>	<table> <tr> <td>Melting point (ring & ball) (NF EN 1427).....</td> <td>125 °C</td> </tr> <tr> <td>Penetration at 25 °C (NF EN 1426).....</td> <td>40 1/10⁹ mm</td> </tr> <tr> <td>Cold bend 20 mm ø (UEAtc) no cracking at.....</td> <td>- 25 °C</td> </tr> <tr> <td>Elongation at break.....</td> <td>1500 %</td> </tr> </table>	Melting point (ring & ball) (NF EN 1427).....	125 °C	Penetration at 25 °C (NF EN 1426).....	40 1/10 ⁹ mm	Cold bend 20 mm ø (UEAtc) no cracking at.....	- 25 °C	Elongation at break.....	1500 %
Melting point (ring & ball) (NF EN 1427).....	125 °C								
Penetration at 25 °C (NF EN 1426).....	40 1/10 ⁹ mm								
Cold bend 20 mm ø (UEAtc) no cracking at.....	- 25 °C								
Elongation at break.....	1500 %								
CHARACTERISTICS <i>Finished product</i>	<table> <tr> <td>Cold Bend 20 mm ø (UEAtc) no cracking at.....</td> <td>- 20 °C</td> </tr> <tr> <td>Free shrinkage (NF EN 1107-1)</td> <td>< 5%</td> </tr> <tr> <td>Slump resistance (UEAtc) vertical.....</td> <td>100 °C</td> </tr> </table>	Cold Bend 20 mm ø (UEAtc) no cracking at.....	- 20 °C	Free shrinkage (NF EN 1107-1)	< 5%	Slump resistance (UEAtc) vertical.....	100 °C		
Cold Bend 20 mm ø (UEAtc) no cracking at.....	- 20 °C								
Free shrinkage (NF EN 1107-1)	< 5%								
Slump resistance (UEAtc) vertical.....	100 °C								