

PRODUCT DATA SHEET

n° of certification organisation: 0679
Year mark was 1st fixed : 2006

Technical ref:

AT FORCE

ARMA CPV

DESCRIPTION

ARMA CPV is a polyester reinforced elastomeric modified bituminous membrane, self-protected with a mineral surface. The selvedge is 7cm wide.

USE

Cap sheet for details.

APPLICATION METHOD

Torched.

STORAGE

Rolls to be stored upright and away from heat.

COMPOSITION (indicative)

Reinforcement (gm/m ²) :	Stabilised polyester	120
Binder (gm/m ²) :	Elastomer	3,750
Surface finish (gm/m ²) :	Mineral slates	1,000
Under surface finish (gm/m ²) :	Thermofusible film	10

CHARACTERISTICS

	STANDARD(BS)	UNITS	VALUES	Tolerance		
				Min	Max	
Dimensions	EN 1848-1	Length	8	-1%		
		Width	1	-1%		
		Straightness	Pass			
	EN 1849-1	Nominal roll weight	42.9			
		Thickness (selvedge)	3.90	3.70	4.10	
Visible defects	EN 1850-1	New product	None			
		After ageing to EN 1297	NA			
Adhesion of granules	EN 12039	%	15	0	30	
Resistance to tearing (nail shank)	EN 12310-1	Longitudinal	NA	-	-	
		Cross direction	NA	-	-	
Tensile properties : maximum tensile force	EN 12311-1	Longitudinal	450	320	580	
		Cross direction	270	250	290	
Tensile properties : elongation	EN 12311-1	Longitudinal	25	10	40	
		Cross direction	25	10	40	
Peel resistance of joint	EN 12316-1	Maximum force	Selvedge	NA	-	-
			End joint	NA	-	-
		Average force	Selvedge	NA	-	-
			End joint	NA	-	-
Shear resistance of joint	EN 12317-1	Maximum force	Selvedge	NA	-	-
			End joint	NA	-	-
Flexibility at low temperature	EN 1109	Surface	-10	≤		
		Under surface	-10	≤		
Flow resistance at elevated temperature	EN 1110	New product	90	≥		
		After ageing to EN 1296	100	90	110	
Resistance to impact	EN 12691	mm	NA	≤		
Resistance to static loading	EN 12730 (A)	kg	NA	≥		
Dimensional stability	EN 1107-1	%	0.3	≤		
Form stability under cyclic temperature change	EN 1108	%	NA			
Water vapour transmission properties	EN 1931	New product	-	μ=20000		
		After ageing to EN 1296	-	NA		
Watertightness	EN 1928	New product	-	Pass	<10 kPa	
		After ageing to EN 1296	-	NA		
Watertightness after stretching at low temperature	EN 13897	%	NA			
Reaction to fire	EN 13501-1	-	F			
Resistance to root penetration	EN 13948	-	NA			
Dangerous substances consult :	-	-	None			

http://europa.eu.int/comm/enterprise/construction/internal/dangsub/dangmain.htm
NA=not applicable due to use of product.

The manufacturer reserves the right to modify, at any time, the characteristics of its products.