

PRODUCT DATA SHEET

n° of certification organisation: 0679
Year mark was 1st fixed : 2006

CAMINAXTER / AXTEP

Technical ref:
▶ AT ALPAL

DESCRIPTION

→ CAMINAXTER is a stabilised polyester reinforced, elastomeric (SBS) modified bituminous waterproofing membrane. Its surface is finished with ceramic granules of a specific colour.

USE

→ Walkway material for flat roof waterproofing systems.

APPLICATION METHOD

→ Fully bonded by torching on to the waterproofing system, normally with butt joints.

STORAGE

→ Rolls to be stored upright and away from heat.

COMPOSITION (indicative)

Reinforcement (gm/m ²) :	Stabilised polyester	180
Binder (gm/m ²) :	SBS elastomer	3,730
Surface finish (gm/m ²) :	Mineral granules	1,200
Under surface finish (gm/m ²) :	Thermofusible film	10

CHARACTERISTICS

	STANDARD(BS)	UNITS	VALUES	Tolerance		
				Min	Max	
Dimensions	EN 1848-1	Length	8	-1%		
		Width	1	-1%		
		Straightness	-	Pass		
	EN 1849-1	Nominal roll weight	43.2			
		Thickness (on finished product)	3.95	3.80	4.10	
Visible defects	EN 1850-1	New product	-	None		
		After ageing to EN 1297	-	NA		
Adhesion of granules	EN 12039	%	15	0	30	
Resistance to tearing (nail shank)	EN 12310-1	Longitudinal	NA	-	-	
		Cross direction	NA	-	-	
Tensile properties : maximum tensile force	EN 12311-1	Longitudinal	690	570	810	
		Cross direction	540	440	640	
Tensile properties : elongation	EN 12311-1	Longitudinal	40	30	50	
		Cross direction	50	40	60	
Peel resistance of joint	EN 12316-1	Maximum force	Selvage	NA	-	-
			End joint	NA	-	-
		Average force	Selvage	NA	-	-
			End joint	NA	-	-
Shear resistance of joint	EN 12317-1	Maximum force	Selvage	NA	-	-
			End joint	NA	-	-
Flexibility at low temperature	EN 1109	Surface	-16	≤		
		Under surface	-16	≤		
Flow resistance at elevated temperature	EN 1110	New product	100	≥		
		After ageing to EN 1296	110	100	120	
Resistance to impact	EN 12691	mm	20	≤		
Resistance to static loading	EN 12730 (A)	kg	20	≥		
Dimensional stability	EN 1107-1	%	0.5	≤		
Form stability under cyclic temperature change	EN 1108	%	NA			
Water vapour transmission properties	EN 1931	New product	-	μ=20000		
		After ageing to EN 1296	-	NA		
Watertightness	EN 1928	New product	-	Pass	<10 kPa	
		After ageing to EN 1296	-	NA		
Watertightness after stretching at low temperature	EN 13897	%	NA			
Reaction to fire	EN 13501-1	-	F			
Resistance to root penetration	EN 13948	-	NA			
Dangerous substances consult :	-	-	None			

http://europa.eu.int/comm/enterprise/construction/internal/dangsub/dangmain.htm
NA=not applicable due to use of product.

The manufacturer reserves the right to modify, at any time, the characteristics of its products.