



Technical Data Sheet

Datasheet 14.9.09
Product Code: 1611002

Axter Limited

West Road Ransomes Europark
Ipswich Suffolk IP3 9SX
Tel (01473) 724056 Fax (01473) 723263
Email info@axterltd.co.uk

www.axter.co.uk

NB: The manufacturer reserves the right without prior notice to modify the composition of his products. Characteristics provided in this publication derive from data obtained under controlled test conditions. AXTER Limited makes no warranties, express or implied as to the properties and performance under any variations from such conditions in actual construction.

HYRA-STIK

INTRODUCTION	Polyurethane, honey-coloured, liquid adhesive
USAGE	Adhesive for thermal insulation boards (EPS, PUR and PIR).
PACKAGING	6.5kg can.
STORAGE	To be stored away from heat and naked flame. Maximum shelf life (sealed and in original packaging): 9 months. Manufacture and 'Use by' dates are shown on the can.
COMPOSITION	Single component liquid polyurethane.
CHARACTERISTICS	Density 1120 kg/m ³ ± 10 Viscosity at 20°C (SL 002A) 7000 mPa.s ± 1500
GENERAL	<ul style="list-style-type: none">➤ Coverage: 100 - 300 gm/m².➤ Applied in strips (25 to 75 gm/ml) at a rate of 4 strips per metre. At roof edges and upstands, increase rate by 1.5.➤ Insulation boards must be laid immediately after the adhesive has been applied, before a skin forms on the surface of the strips.➤ Drying time is between 2 and 6 hours, depending on temperature and humidity.➤ Do not use in temperatures below 5°C. <p>Safety precautions to be followed when using this product are described in the HYRA-STIK COSHH sheet.</p>

The manufacturer reserves the right to modify, at any time, the characteristics of their products. The information given above is indicative only with tolerances in accordance with current practice.