

PRODUCT DATA SHEET

n° of certification organisation: 0679
Year mark was 1st fixed : 2006

Technical ref:
▶ AT HYRANGER

HYRENE (HYRANGER) 30

DESCRIPTION

→ HYRANGER 30 is a glass-fibre reinforced SBS elastomeric modified bituminous waterproofing membrane. Its surface is finished with coloured mineral chippings or ceramic granules. Minimum selvedge width is 6cm.

USE

→ Cap sheet for use in multi-layer waterproofing systems. Part of the HYRANGER and HYRANGER TS waterproofing system for flat roofs.

APPLICATION METHOD

→ Pour and roll.

STORAGE

→ Rolls to be stored upright and away from heat.

COMPOSITION

(indicative)

Reinforcement (gm/m ²) :	Glass-fibre	50
Binder (gm/m ²) :	SBS elastomer	2,140
Surface finish (gm/m ²) :	Mineral slates or granules	1,000 1,200
Under surface finish (gm/m ²) :	Sand	300

CHARACTERISTICS

	STANDARD(BS)	UNITS	VALUES	Tolerance		
				Min	Max	
Dimensions	EN 1848-1	Length	10	-1%		
		Width	1	-1%		
		Straightness	Pass			
	EN 1849-1	Nominal roll weight	39.3			
		Thickness (selvedge)	2.30	2.15	2.50	
Visible defects	EN 1850-1	New product	None			
		After ageing to EN 1297	NA			
Adhesion of granules	EN 12039	%	15	0	30	
Resistance to tearing (nail shank)	EN 12310-1	Longitudinal	NA	-	-	
		Cross direction	NA	-	-	
Tensile properties : maximum tensile force	EN 12311-1	Longitudinal	250	200	500	
		Cross direction	150	120	280	
Tensile properties : elongation	EN 12311-1	Longitudinal	3	2	4	
		Cross direction	3	2	4	
Peel resistance of joint	EN 12316-1	Maximum force	Selvedge	NA	-	-
			End joint	NA	-	-
		Average force	Selvedge	NA	-	-
			End joint	NA	-	-
Shear resistance of joint	EN 12317-1	Maximum force	Selvedge	NA	-	-
			End joint	NA	-	-
Flexibility at low temperature	EN 1109	Surface	-16	≤		
		Under surface	-16	≤		
Flow resistance at elevated temperature	EN 1110	New product	100	≥		
		After ageing to EN 1296	110	100	120	
Resistance to impact	EN 12691	mm	NA	≤		
Resistance to static loading	EN 12730 (A)	kg	NA	≥		
Dimensional stability	EN 1107-1	%	0.1	≤		
Form stability under cyclic temperature change	EN 1108	%	NA			
Water vapour transmission properties	EN 1931	New product	μ=20000			
		After ageing to EN 1296	NA			
Watertightness	EN 1928	New product	Pass	<10 kPa		
		After ageing to EN 1296	NA			
Watertightness after stretching at low temperature	EN 13897	%	NA			
Reaction to fire	EN 13501-1	-	F			
Resistance to root penetration	EN 13948	-	NA			
Dangerous substances consult : http://europa.eu.int/comm/enterprise/construction/internal/dangsub/dangmain.htm	-	-	None			

NA=not applicable due to use of product.

The manufacturer reserves the right to modify, at any time, the characteristics of its products.