



# Technical Data Sheet

Datasheet 11.12.09  
Product Code: 1966001  
Technical Reference: Starcoat R Cahier des Charges

## Axter Limited

West Road Ransomes Europark  
Ipswich Suffolk IP3 9SX  
Tel (01473) 724056 Fax (01473) 723263  
Email info@axterltd.co.uk

[www.axter.co.uk](http://www.axter.co.uk)

NB: The manufacturer reserves the right without prior notice to modify the composition of his products. Characteristics provided in this publication derive from data obtained under controlled test conditions. AXTER Limited makes no warranties, express or implied as to the properties and performance under any variations from such conditions in actual construction.

## MATCOAT JD

**MATCOAT JD is an EPDM rubber strip reinforced on its underside by a non-woven polyester.**

### USE

Reinforcement of movement joints

### PACKAGING

Rolls of 25m x 0.15m

### STORAGE

- Store in a cool, well ventilated place
- Protect from heat, direct sunlight and extremes of temperature.
- Store at temperatures between 5°C and 35°C

### CHARACTERISTICS

Thickness (EN ISO 2286-3)	0.35mm
Surface mass (DIN 53352)	>250g/m <sup>2</sup>
Tensile force (DIN 53857): longitudinal/ cross direction	500/50 N/5cm
Burst strength (DIN 53861)	2 bars/cm <sup>2</sup>
Water vapour permeability (DIN 7783-2)	7.90 sd
Reinforced rubber: resistance to tearing - longitudinal	20%
Rubber: resistance to tearing - longitudinal	100%

### GENERAL

MATCOAT R is sandwiched between two layers of STARCOAT R.

Use scissors to cut appropriately sized pieces for the details and apply to the first layer of STARCOAT R.

Ensure a minimum overlap of 10mm between each piece of MATCOAT JD.

Apply pressure with a dry brush to ensure full bonding with no blistering.