

# PRODUCT DATA SHEET

n° of certification organisation: 0679  
Year mark was 1<sup>st</sup> fixed : 2006

**Technical ref:**

▶ AT FORCE

## MATFIX

### DESCRIPTION

→ MATFIX is a glass-fibre reinforced SBS elastomeric modified bituminous waterproofing membrane. It is finished on its undersurface with a polyester mat.

### USE

→ Mechanically fixed base layer in torch-on waterproofing systems on timber, cellular concrete, insulation board or existing waterproofing deck.

### APPLICATION METHOD

→ Mechanically fastened.

### STORAGE

→ Rolls to be stored upright and away from heat.

### COMPOSITION

(indicative)

Reinforcement (gm/m <sup>2</sup> ) :	Glass-fibre	50
Binder (gm/m <sup>2</sup> ) :	SBS elastomer	1,400
Surface finish (gm/m <sup>2</sup> ) :	Thermofusible film	10
Under surface finish (gm/m <sup>2</sup> ) :	Polyester mat	100

### CHARACTERISTICS

	STANDARD(BS)	UNITS	VALUES	Tolerance		
				Min	Max	
Dimensions	EN 1848-1	Length	20		-1%	
		Width	1		-1%	
		Straightness	Pass			
	EN 1849-1	Nominal roll weight	31.1			
		Thickness (on finished product)	1.6	-	-	
Visible defects	EN 1850-1	New product	None			
		After ageing to EN 1297	NA			
Adhesion of granules	EN 12039	%	NA	-	-	
Resistance to tearing (nail shank)	EN 12310-1	Longitudinal	220	200	320	
		Cross direction	180	170	260	
Tensile properties : maximum tensile force	EN 12311-1	Longitudinal	400	300	500	
		Cross direction	300	200	400	
Tensile properties : elongation	EN 12311-1	Longitudinal	25	20	45	
		Cross direction	25	20	45	
Peel resistance of joint	EN 12316-1	Maximum force	Selvedge	NA	-	-
			End joint	NA	-	-
		Average force	Selvedge	NA	-	-
			End joint	NA	-	-
Shear resistance of joint	EN 12317-1	Maximum force	Selvedge	NA	-	-
			End joint	NA	-	-
Flexibility at low temperature	EN 1109	Surface	-16		≤	
		Under surface	-16		≤	
Flow resistance at elevated temperature	EN 1110	New product	100		≥	
		After ageing to EN 1296	NA	-	-	
Resistance to impact	EN 12691	mm	NA		≤	
Resistance to static loading	EN 12730 (A)	kg	NA		≥	
Dimensional stability	EN 1107-1	%	0.3		≤	
Form stability under cyclic temperature change	EN 1108	%	NA			
Water vapour transmission properties	EN 1931	New product	-	μ=20000		
		After ageing to EN 1296	-	NA		
Watertightness	EN 1928	New product	-	Pass	<10 kPa	
		After ageing to EN 1296	-	NA		
Watertightness after stretching at low temperature	EN 13897	%	NA			
Reaction to fire	EN 13501-1	-	F			
Resistance to root penetration	EN 13948	-	NA			
Dangerous substances consult : <a href="http://europa.eu.int/comm/enterprise/construction/internal/dangsub/dangmain.htm">http://europa.eu.int/comm/enterprise/construction/internal/dangsub/dangmain.htm</a> NA=not applicable due to use of product.	-	-	None			