



Technical Data Sheet

Datasheet 11.12.09
Product Code: 196100X
Technical Reference: Starcoat R Cahier des Charges

Axter Limited

West Road Ransomes Europark
Ipswich Suffolk IP3 9SX
Tel (01473) 724056 Fax (01473) 723263
Email info@axterltd.co.uk

www.axter.co.uk

NB: The manufacturer reserves the right without prior notice to modify the composition of his products. Characteristics provided in this publication derive from data obtained under controlled test conditions. AXTER Limited makes no warranties, express or implied as to the properties and performance under any variations from such conditions in actual construction.

PRIMCOAT

Primcoat is a polyurethane-based bituminous, solvent-free, amber coloured primer.

USAGE

Priming coat for concrete decks, humid mineral slates, existing bituminous roofs, ferrous and non-ferrous metals, plastics.
Coverage from 100 to 200 gm/m² maximum.
Particularly suitable when use of flame is prohibited.
Can be diluted with 3-7% mek or xylene thinner.

PACKAGING

Metal cans: 1kg or 4kg.

STORAGE

- Store in a cool, well ventilated place.
- Protect from heat, sunshine, rain and frost.
- Maximum shelf life (sealed in original packaging): 6 months.

CHARACTERISTICS

Density	1.35 ± 0.05
Dry extract	>100%
Viscosity to 25°C (NFT 30014)	2500 Cp
Flash point	>42°C
Drying time	Approx. 6 hours (at 25°C and 55% HR)

GENERAL

Open the two cans Resin A and Hardener B. Pour part B into part A. Stir well for a minimum of 3 minutes immediately prior to application with a mechanical stirrer 300 to 400 turns/minute with a helical blade. The mixture should be applied in one or two layers depending on the porosity of the deck and the thickness required. Application is by brush or roller in two layers, the second at right angles to the first, or rubber scraper.
Tools, other equipment and spillages must be cleaned immediately with acetone, mek or xylene.
Consumable items such as brushes, adhesives, etc, are generally not suitable for re-use and must be discarded after each prolonged break in application.