



TECHNICAL DATA SHEET

February 2014
 Product Code: 1982001

VERNIS ANTAC ST

INTRODUCTION	VERNIS ANTAC ST is a ready-to-use, rapid drying, bituminous primer								
USAGE	<ul style="list-style-type: none"> To prime all types of deck prior to the installation of the w waterproofing system. To protect basements and underground works (foundation walls), etc. Average coverage: 5-6 m² / litre / layer. 								
PACKAGING	<ul style="list-style-type: none"> 25 litre drum 5 litre drum 400ml aerosol 200 litre drum 								
STORAGE	Drums to be stored upright in a cool, ventilated place, protected from heat and kept away from flames or any source of electrostatic charges. Maximum shelf life from date of manufacture, unsealed in its original packaging: 1 year.								
COMPOSITION	Solvent based bitumen Free from toluene Rapid drying, aromatic solvents								
CHARACTERISTICS	<table> <tr> <td>Density</td> <td>0.92 ± 0.05</td> </tr> <tr> <td>Dry extract at 105°C</td> <td>50% ± 2%</td> </tr> <tr> <td>Viscosity @ 25°C (NFT 30014) CF N°4</td> <td>20 to 40 s</td> </tr> <tr> <td>Flash point</td> <td>23°C</td> </tr> </table> <p>Drying time: 60 to 90 minutes (may vary depending on weather conditions).</p>	Density	0.92 ± 0.05	Dry extract at 105°C	50% ± 2%	Viscosity @ 25°C (NFT 30014) CF N°4	20 to 40 s	Flash point	23°C
Density	0.92 ± 0.05								
Dry extract at 105°C	50% ± 2%								
Viscosity @ 25°C (NFT 30014) CF N°4	20 to 40 s								
Flash point	23°C								
COMMENTS	Safety precautions must be taken while using the product. These are listed in the VERNIS ANTAC ST safety sheet. Do not eat, drink or eat while using the product. VERNIS ANTAC ST is very toxic; do not inhale fumes or consume and avoid contact with the skin. Do not dispose of into drains.								

The manufacturer reserves the right without prior notice to modify the composition of these products. Characteristics provided in this publication derive from data obtained under controlled test conditions. Axter Ltd makes no warranties, express or implied, as to the properties and performance under any variations from such conditions in actual construction.

